



FINE PERLITE SIEVE ANALYSIS FORM

Production Date: Wednesday, May 22, 2024
Ore Used: Socorro 71S
Sample Wt: 50 grams

Used In: _____

QC Tech: cw

Batch/Pallet #	Bulk Density		Sieve No.													
			#4		#8		#16		#30		#50		#100		Pan	
10	7.8	pcf	0.00	g	1.70	g	22.40	g	39.80	g	47.30	g	49.60	g	50.00	g
	125.4	g/L	0.0	%	3.4	%	44.8	%	79.6	%	94.6	%	99.2	%	100.0	%
		pcf		g		g		g		g		g		g		g
		g/L		%		%		%		%		%		%		%
		pcf		g		g		g		g		g		g		g
		g/L		%		%		%		%		%		%		%
		pcf		g		g		g		g		g		g		g
		g/L		%		%		%		%		%		%		%
		pcf		g		g		g		g		g		g		g
		g/L		%		%		%		%		%		%		%
		pcf		g		g		g		g		g		g		g
		g/L		%		%		%		%		%		%		%
		pcf		g		g		g		g		g		g		g
		g/L		%		%		%		%		%		%		%
		pcf		g		g		g		g		g		g		g
		g/L		%		%		%		%		%		%		%
Specs:	7.5/12		0		0/15		15/60		40/80		75/95		90/100			
Average:	7.8		0.0%		3.4%		44.8%		79.6%		94.6%		99.2%		100.0%	

Remarks: Per Strong 1.020, 1.090 and ASTM C332